


SANCO - Straight lengths

| Temper: **hard** or **half-hard**

| Dimensions ex stock, many further sizes available e.g. UK table X/Y, ASTM ¼" to 11"



Tube	Dimension mm	Temper	Operating pressure* bar	Nominal weight kg/m	Water content l/m	Tube length per litre m/l
	6 x 1.0	h, hh	194	0.140	0.013	79.58
	8 x 1.0	h, hh	139	0.196	0.028	35.37
	10 x 1.0	h, hh	109	0.252	0.050	19.89
	12 x 1.0	h, hh	89	0.308	0.079	12.73
	14 x 1.0	h, hh	76	0.363	0.113	8.84
	15 x 1.0	h, hh	70	0.391	0.133	7.53
	15 x 1.5	h	109	0.566	0.113	8.84
	16 x 1.0	h, hh	66	0.419	0.154	6.50
	18 x 1.0	h, hh	57	0.475	0.201	4.97
	18 x 1.5	h	87	0.692	0.177	5.66
	22 x 1.0	h, hh	46	0.587	0.314	3.18
	22 x 1.1	hh	51	0.643	0.308	3.25
	22 x 1.5	h, hh	70	0.860	0.284	3.53
	28 x 1.0	h, hh	36	0.756	0.531	1.88
	28 x 1.2	hh	43	0.899	0.515	1.94
	28 x 1.5	h, hh	54	1.110	0.491	2.04
	35 x 1.0	h	28	0.951	0.855	1.17
	35 x 1.2	h	34	1.134	0.835	1.20
	35 x 1.5	h	43	1.410	0.804	1.24

* Calculated with 3.5 times safety coefficient on the basis of soft copper tubes with Rm 200 N/mm² at an operating temperature of 100 °C

hh = half-hard straight lengths R 250

h = hard drawn straight lengths R 290